



中国认可  
国际互认  
检测  
TESTING  
CNAS L1842



佛山中纺联检验技术服务有限公司  
CNTAC Testing Service Co.,Ltd.(Foshan)

<b>Testing Report</b>	Security website: <a href="http://www.fcl-sz.org.cn">www.fcl-sz.org.cn</a> Security code: 6245716545
Report No: ZFLJ2642376A	Page 1 of 8



### Applicant Information

Applicant Name : BNX CONVERTING,LLC.  
Applicant Address : 16727 Park Row Houston TX 77084 USA  
Manufacturer : BNX CONVERTING,LLC.

### Sample Information

Sample Description : A96 Duckbill mask  
Style No. : A96  
Brand : BNX Converting LLC  
Sample Quantity : 65 pieces  
Size specification : 240mmX95mm  
Material Components : 6 layers 1. 50gsm spunbond pp 2. 25gsm meltblown 3. 25gsm meltblown  
4.15gsm spunbond pp 5. 25gsm skin friendly (hydrophilic) nonwoven 6. 25gsm  
skin friendly (hydrophilic) nonwoven

- Sample Receiving Date : 2020-08-14  
- Report Date : 2020-08-26  
- The original sample is stucked on the last paper.

### Test Performed

Judgement according to:  
GB 2626-2019 Respiratory protection— Non-powered air-purifying particle respirator .  
- Selected test(s) as requested by applicants. For details, refer to attached page(s).

### Pronounce

The results shown in this report refer only to sample(s) tested unless otherwise stated.  
All the items are performed in the standard conditions, except the noted cases.  
Except for the requirement of the client, the test results and the conformity judgement of this report do not take the uncertainty of the test results into account.

Signed for and on behalf of  
**CNTAC Testing Service Co.,Ltd.(Foshan)**

Approved by

张志荣





中国认可  
国际互认  
检测  
TESTING  
CNAS L1842




<b>Testing Report</b>	Security website: www.fcl-sz.org.cn Security code: 6245716545
Report No: ZFLJ2642376A	Page 2 of 8



--- Test Result ---

Requirements	Test Result	Judgement
<b>1.Basic requirements</b> <u>GB 2626-2019 Section 5.1</u>		
<b>The materials shall meet the following requirements:</b>		Pass
Materials in direct contact with the face shall be harmless to the skin	Accordance	
The filter material shall be harmless to human body	Accordance	
The materials used shall have sufficient strength and shall not be damaged and deformed in normal use	Accordance	
Wear without obvious tenderness or tingling	Accordance	
<b>The structural design shall meet the following requirements:</b>		
It shall not be easy to cause structural damage, and the design, composition and installation of components shall not pose any danger to users	Accordance	
The design of head harness shall be elastic material or adjustable, easy to wear and remove, and it shall be able to firmly fix the facepiece on the face, without obvious compression or tenderness	Accordance	
It shall not affect visual field obviously	Accordance	
The structure of the disposable facepiece shall be able to ensure the fit with the face, and should not appear deformation in normal use	Accordance	





中国认可  
国际互认  
检测  
TESTING  
CNAS L1842



佛山中纺联检验技术服务有限公司  
CNTAC Testing Service Co.,Ltd.(Foshan)

<b>Testing Report</b>	Security website: <a href="http://www.fcl-sz.org.cn">www.fcl-sz.org.cn</a> Security code: 6245716545
Report No: ZFLJ2642376A	Page 3 of 8



Test Result

Requirements

Judgement

**2.Functional Performance** GB 2626-2019 Section 6.16

Respirator Information		
Model and specification	Standard with Duckbill Folding Style with Headband Attachment	
Brand	No information provided by the customer	
Manufacturer Information	BNX Converting,LLC. 16727 Park Row Houston,TX 77084 USA	
Evaluation Report		
Before testing functional performance, the respirator has completed all laboratory performance tests and is confirmed to be harmless to human subjects.		
Performance category	Evaluation Content	
Categories (A) directly related to security	Respiration	Good patency, comfortable air supply, large ventilation
	Vision	No obvious effect on visual field
	Security	The head harness is strong
	Communication Capability	Clear pronunciation, clear hearing, the instructions can be clearly heard, and according to the instructions quickly make the correct response
	Control Device	High intuitive adjustment, easy to understand, easy to operate, low possibility of misoperation or accidental operation
	Activity	High freedom degree of head movement
Categories (B) not directly related to security	Convenience of Use	Convenient to wear, convenient to take off
	Comfort Degree	Facial comfort, moderate thermal comfort, feel comfortable after use
	Maintenance and storage	Easy to maintain and store
	Instruction for use	Usage method is easy to understand, maintenance and storage is easy to understand
	Total evaluation	Acceptable level is moderate






中国认可  
国际互认  
检测  
TESTING  
CNAS L1842



<b>Testing Report</b>	Security website: <a href="http://www.fcl-sz.org.cn">www.fcl-sz.org.cn</a> Security code: 6245716545
Report No: ZFLJ2642376A	Page 4 of 8



	Test Result	Requirements	Judgement
<b>3. Appearance Inspection</b> <u>GB 2626-2019 Section 6.1 and 6.2</u>			
Result	Accordance	The surface should not be damaged, deformation and other obvious defects.	Pass
	Accordance	Component materials and structures shall be able to withstand normal operating conditions and possible temperature, humidity and mechanical shocks.	
	Accordance	After temperature and humidity pretreatment, components should not fall off, damage and deformation.	
<b>4. Filtration Efficiency</b> <u>GB 2626-2019 Section 6.3</u>			
Air flow:85L/min,Aerosol: NaCl			
Unit: <%>			
Before pretreatment		(KN95) ≥ 95.0	Pass
sample 1#	99.2		
sample 2#	99.3		
sample 3#	99.4		
sample 4#	99.5		
sample 5#	99.7		
sample 6#	99.6		
sample 7#	99.5		
sample 8#	99.3		
sample 9#	99.3		
sample 10#	99.1		
sample 11#	99.2		
sample 12#	99.2		
sample 13#	99.5		
sample 14#	99.3		
sample 15#	99.2		
After pretreatment			
sample 1#	99.2		
sample 2#	99.8		
sample 3#	99.3		
sample 4#	99.7		
sample 5#	99.2		
Minimum	99.1		





中国认可  
国际互认  
检测  
TESTING  
CNAS L1842



<b>Testing Report</b>	Security website: <a href="http://www.fcl-sz.org.cn">www.fcl-sz.org.cn</a> Security code: 6245716545
Report No: ZFLJ2642376A	Page 5 of 8



Test Result	Requirements	Judgement
-------------	--------------	-----------

**5. Inward Leakage** GB 2626-2019 Section 6.4

50 out of the 50 individual exercise results for total inward leakage are not greater than 11%.

KN95  
At least 46 out of the 50 individual exercise results (i.e. 10subjects x 5 exercise) for total inward leakage shall be not greater than 11%.

Pass

10 out of 10 individual wearer arithmetic means for the total inward leakage are not greater than 8%.

At least 8 out of 10 individual wearer arithmetic means for the total inward leakage shall be not greater than 8%.

Remark: Inward leakage detailed test data on appendix page.

**6. Inhalation Resistance** GB 2626-2019 Section 6.5

Air flow:85L/min  
Unit: <Pa>

Before pretreatment	
sample 1#	82.1
sample 2#	85.6
After pretreatment	
sample 1#	88.3
sample 2#	86.8
Maximum	88.3

≤ 210

Pass

**7. Exhalation Resistance** GB 2626-2019 Section 6.6

Air flow:85L/min  
Unit: <Pa>

Before pretreatment	
sample 1#	70.2
sample 2#	76.5
After pretreatment	
sample 1#	78.8
sample 2#	75.3
Maximum	78.8

≤ 210

Pass

**8. Dead Space** GB 2626-2019 Section 6.9

Unit: <%>

Volume fraction of carbon dioxide 0.2

Volume fraction of carbon dioxide ≤ 1 Pass





中国认可  
国际互认  
检测  
TESTING  
CNAS L1842



<b>Testing Report</b>	Security website: <a href="http://www.fcl-sz.org.cn">www.fcl-sz.org.cn</a> Security code: 6245716545
Report No: ZFLJ2642376A	Page 6 of 8



Test Result	Requirements	Judgement
-------------	--------------	-----------

**9. Visual field** GB 2890-2009 section 6.8

Below visual field	68.7°	Below visual field ≥ 35°	Pass
Binocular visual field	97.3%	Binocular visual field ≥ 65%	

**10. Head harness** GB 2626-2019 Section 6.11


For disposable facepiece, tension 10N for 10s

Before pretreatment		No slippage or fracture shall occur	Pass
No slippage and fracture			
After pretreatment			
No slippage and fracture			

**11. Flammability** GB 2626-2019 Section 6.15

Unit: <s>

After flame time		After flame time ≤ 5	Pass
Before pretreatment			
sample 1#	0		
sample 2#	0		
After pretreatment			
sample 1#	0		
sample 2#	0		





中国认可  
国际互认  
检测  
TESTING  
CNAS L1842



佛山中纺联检验技术服务有限公司  
CNTAC Testing Service Co.,Ltd.(Foshan)

<b>Testing Report</b>	Security website: <a href="http://www.fcl-sz.org.cn">www.fcl-sz.org.cn</a> Security code: 6245716545
Report No: ZFLJ2642376A	Page 7 of 8



**Appendix Page :**

Inward Leakage ( Disposable mask )		Individual exercise 1 TIL (%)	Individual exercise 2 TIL (%)	Individual exercise 3 TIL (%)	Individual exercise 4 TIL (%)	Individual exercise 5 TIL (%)	Mean individual wearer TIL (%)
The sample before pretreatment	Individual wearer 1	2.9	3.6	4.0	4.2	4.4	3.8
	Individual wearer 2	3.9	4.4	4.8	5.1	5.3	4.7
	Individual wearer 3	4.6	5.1	5.5	5.6	5.6	5.3
	Individual wearer 4	4.5	4.6	4.7	5.0	5.3	4.8
	Individual wearer 5	6.5	6.5	6.6	6.9	6.9	6.7
The sample after pretreatment	Individual wearer 6	5.2	5.3	5.8	6.1	6.6	5.8
	Individual wearer 7	4.5	4.9	5.0	5.5	6.6	5.3
	Individual wearer 8	5.6	5.7	5.9	6.2	6.5	6.0
	Individual wearer 9	6.8	6.9	7.5	7.6	7.7	7.3
	Individual wearer 10	2.2	2.4	1.6	2.8	1.6	2.1





中国认可  
国际互认  
检测  
TESTING  
CNAS L1842



佛山中纺联检验技术服务有限公司  
CNTAC Testing Service Co.,Ltd.(Foshan)

<b>Testing Report</b>	Security website: <a href="http://www.fcl-sz.org.cn">www.fcl-sz.org.cn</a> Security code: 6245716545
Report No: ZFLJ2642376A	Page 8 of 8



**Original Sample**



===== End of Report =====

